


Ducokote HIGH QUALITY SYNTHETIC ENAMEL

A high-quality synthetic enamel designed for both interior and exterior surfaces. This decorative embossed coating not only adds visual appeal but also provides insulation against moisture, sound, and thermal influences. Its resistance to adverse weather conditions ensures long-lasting protection and durability.



SPECIFICATIONS

Base	Alkyd
Appearance	Thick liquid
Hue	White and shades
Viscosity	1800–2500 mPa•s at 23°C
Density	1.17 + 0,02 gr/cm ³
Gloss 60°	85
Solids	1.17 + 0,02 gr/cm ³
Ideal application and drying temperature	85
Surface Drying	2–3 hr
Deep drying	24 hr
Recoating Time (*)	24 hr
Yield	12–14 m ² /lt per coat
Dilution	5% with White Spirit or Nitro Thinner

NOTE (*): The exact time depends on the temperature and relative humidity prevailing during application and drying.

USES

Ideal for surfaces from:

- Metal

CHARACTERISTICS

- Moisture Insulation
- Sound & Thermal Insulation
- Weather Resistant

TOOLS CLEANING

While working, keep the tools "wet" in the container or in the paint bucket. Drain off the paint well from tools into the container and clean them with White Spirit.

STORAGE

One year in closed container, at temperatures between 5° C – 35° C.

SURFACE PREPARATION

- It is applied on dry, clean surfaces free of materials that prevent adhesion.
- Application's success depends on the proper preparation of the surface and the correct application of the material.
- Remove silicone or oils from the metal surface with solvent.
- Prime surface with METAL PROTECTOR.

APPLICATION

- Apply DUCOKOTE on the surface in two coats
 - To adjust the fluidity, it can be diluted by adding 5% with White Spirit or Nitro Thinner.
 - The second coat must be applied after the first one has dried.
 - Ducokote boasts very good gloss and hardness, offering high performance and fast drying times.
- Its impressive chemical and mechanical resistance make it a reliable choice for a wide range of applications.

RESTRICTIONS

- Do not apply at temperatures below 5°C or above 35°C.
- Do not apply when the air relative humidity is higher than 80%.
- Wet surfaces should be allowed to dry thoroughly before application.

VOC CATEGORY

Product Category A/i (SB) 'One-pack performance coatings' of the EU legislation 2004/42/EU. Maximum limit VOC value of category: 500gr/ltr. Maximum VOC concentration of ready to use product 499 gr/ltr.