


LANKOTE

COATINGS

Lankryl W200

HIGH RESISTANCE 100% ACRYLIC PAINT

A high-resistance 100% acrylic paint specifically designed for exterior use on new or old building surfaces, such as concrete, plaster, bricks, and more. This siloxane-based acrylic paint offers excellent grip and an amazing finish, meeting the highest standards (ELOT 788).



TECHNICAL CHARACTERISTICS

Shades	White, Gray, Blue
Viscosity	7500 – 8000 mPa•s at 23°C
Density	1.50 ± 0,02 gr/cm ³
Gloss 60°	20-40
Surface Drying	30-45min
Recoating Time	6-8hrs
Yield	11-13 m ² /lt
Dilution	5-10% with White Spirit

NOTE (*): (*) The exact time depends on the temperature and relative humidity prevailing during application and drying.

LANKOTE
COATINGS

USES

Ideal for surfaces from:

- Wood
- Plaster
- Concrete
- Brick

CHARACTERISTICS

- High Whiteness
- Weather Resistance
- Good chemical resistance

SURFACE PREPARATION

- It is applied on dry, clean surfaces free of materials that prevent adhesion.
- Application's success depends on the proper preparation of the surface and the correct application of the material.
- For highly absorbent surfaces, prime surface with DESMO SEAL solvent-based primer.

APPLICATION

- Lankryl W200 is applied directly to the concrete surface with a dilution of 15-20% with BRUSH SOLVENT
- Then Apply Lankryl W200 on the surface in two layers.
- To adjust the fluidity, it can be diluted by adding 5-10% BRUSH SOLVENT SL-100 (White spirit).
- The second layer must be applied after the first one has dried.

TOOLS CLEANING

While working, keep the tools "wet" in the container or in the paint bucket. Drain off the paint well from tools into the container and clean them with White Spirit.

STORAGE

One year in closed container, at temperatures between 5° C - 35° C.

RESTRICTIONS

- Do not apply at temperatures below 5°C or above 35°C.
- Do not apply when the air relative humidity is higher than 80%.
- Wet surfaces should be allowed to dry thoroughly before application.
- Freshly painted surface should be protected from cold and moisture for at least 24hr.

VOC CATEGORY

Product of Category A/c (SB) "Exterior walls of mineral substrate" of European Directive 2004/42 / EC.
Category VOC limit value: 430gr/ltr. The maximum VOC content of the ready-to-use product is 429gr/ltr.